



Specialty Paints & Products for
Sign · Branding · Re-Imaging
1.800.421.7961

Q-MASK™ SM4000™ STRIPPABLE MASKING

Q-MASK™ SM4000™ is a water-based transparent Blue strippable masking used in the decoration of plastic signage. **Q-MASK™ SM4000™** is a combination of emulsified resins, plasticizers and distilled water. **Q-MASK™ SM4000™** is 0% VOC and is low in HAPS - hazardous air pollutants.

QHF Environmentally Friendly Product.

APPLICATION:

1.



Safety:

Use only NIOSH approved respirators and personal protection.

Always read the MSDS – Material Safety Data Sheets for safety warnings prior to use.

2.



Storage:

Product must be kept from freezing.


3.



Surface Cleaning:

Remove any existing surface contaminants with **Q-SOLV™ CD4402™** Plastic Cleaner.

4.



Q-MASK™ SM4000™ is ready to spray with no reduction required.

5.



Spray Gun Recommendations:

Airless: .017-.023”mm
Siphon Feed: 2.2 mm” or larger

6.



Spray Application:

Spray apply approximately 20 wet mils minimum.
Utilize a wet film thickness gauge.

7.



Dry Time:

Dry to cut graphics at 75°F-95°F @ 50% R.H. in 12 -24 hours.
Increasing air-flow (fans) speeds up dry time.
Do not force dry **Q-MASK™ SM4000™** with heat.



Specialty Paints & Products for
Sign · Branding · Re-Imaging
1.800.421.7961

Q-MASK™ SM4000™ STRIPPABLE MASKING

- SUITABLE SURFACES:** Polycarbonate, Acrylic, Impact modified acrylic, Acrylic, ABS, CAB, styrene and most flexible and rigid vinyl and most existing dry plastic translucent coatings.
- SURFACE PREPARATION:** Prior to coating with **Q-COAT TC™** Translucent Coating, clean and remove static electricity with **Q-SOLV™ CD4402™** Plastic Cleaner mixed 1:1 by volume with distilled water.
- DRYING SCHEDULE:** 12 –24 hours at 75–95°F (18-35°C).
Increasing air flow (fans) speeds up dry time.
“Do Not Force Dry” **Q-MASK™ SM4000™** with heat.
- STOCK KEEPING COLOR:** Transparent Blue Strippable Masking
- SHELF LIFE:** Six (6) months maximum in unopened containers. One (1) month maximum after container is opened.

FILM CHARACTERISTICS

- CUTTING:** Excellent, no edge feathering
% Elongation at rupture: 250% +
Tensile Strength: 2,000 psi
- RESTICK:** Restick adhesion on polycarbonate, impact modified plastic and acrylics are approximately 0.5-0.7 lb/linear inch assuring physical properties required.
- CHEMICAL RESISTANCE:** Excellent against aromatic, alcohol and aliphatic solvents for short periods of time.
- NOTE:** Do not expose dry **Q-MASK™ SM4000™** dry film to sunlight or water.

Always test surface preparation, primer and topcoat compatibility to determine acceptability before any production run.

Disclaimer: Technical information and suggested uses are believed to be reliable by QH&F Ltd., but such information or suggestions do not constitute a warranty. QH&F Ltd. has no control over the conditions under which the product is stored, handled, used or applied. Buyers must determine for themselves the suitability of each product for their specific use.

® is a registered trademark and ™ is a trademark of Quill Hair & Ferrule LTD. Copyright © 2009. Quill Hair and Ferrule LTD. All Rights Reserved.